

(R)

ACL - 3804
8/2/01
INVC.....

**INVESTIGATIONS ON THE CONDUCTIVITY OF
ORGANOTIN - DOPED POLYETHYLENE OXIDE
POLYMER SYSTEM**

By

Lekshmi Sarojini Amma

**A DISSERTATION SUBMITTED TO UNIVERSITY MALAYA
FOR THE DEGREE OF MASTER OF SCIENCE**

2000

Perpustakaan Universiti Malaya



A510143678

Dinikrofiskan pada..... 21-02-2005
No. Mikrofi..... 15266
Jumlah Mikrofi..... 2

HAMSIAH BT. MOHAMAD ZAHARI
UNIT REPROGRAFI
PERPUSTAKAAN UTAMA
UNIVERSITI MALAYA
UPR

ACKNOWLEDGEMENTS

I would like to express my sincere thanks and gratitude to Associate Professor Dr.Abdul Kariem Arof for his valuable supervision of my masters candidature.

I would also like to gratefully acknowledge my former supervisors

Prof : Radhakrishna and Prof. V.G.Kumar Das for their advice guidance, and encouragement in the early phase of this work..

It is a pleasure to thank Dr Lo Kong Mun of the Dept of Chemistry for his guidance in synthesizing the compounds used in this study.

I am grateful to my family who always has been with me, supporting me even in the hardest of time.

Finally, I would like to express my profound gratitude to my friends for their understanding and constant encouragement during the course of my postgraduate study.

Abstract

Poly(ethylene oxide) (PEO) has been doped with selected organotin compounds. The organotin dopants used were triphenyltin thiocyanate (Ph_3SnSCN) and tetramethylammonium dichlorotriphenylstannate $[\text{Ph}_3\text{SnCl}]^+[\text{Me}_4\text{N}]^+$. Tin incorporation in the polymers was established by several physical techniques. The infrared spectroscopic analysis of the Ph_3SnSCN – doped electrolyte film showed bands at $2080\text{-}2050 \text{ cm}^{-1}$ which are also given by pure Ph_3SnSCN . Different concentrations of organotin doped electrolytes were prepared and conductivity studies on these were performed using impedance spectroscopy. From the measurements it was found that the best conductivity of $7.6 \times 10^{-8} \text{ S/cm}$ was obtained for the composition with PEO :dopant ratio of 90:10 at room temperature. However, it proved possible to increase the conductivity by at least two to three orders of magnitude by the co-addition of plasticizers such as ethylene carbonate (EC) and propylene carbonate (PC), thereby rendering the modified PEO more suitable as an electrolyte material for the solid state batteries. The best conductivity thus attained was of the order of 10^{-5} S/cm for the film of composition Ph_3SnSCN doped PEO : plastizier of 90 :10. The plasticizer component consists of EC and PC in 1:1 ratio. X-ray diffraction analysis confirmed the disruption of the crystalline order of PEO upon interaction with the tin dopants. A similar pattern of results was obtained with tetramethylammonium dichlorotriphenyl stannate as dopant. However, the conductivity was only of the order of 10^{-8} Scm^{-1} and not as good as that given by the Ph_3SnSCN compound. The best conducting sample of triphenyltin thiocyanate-polymer was used in the fabrication of a

primary cell using Sn metal as the anode and a carbon-iodine mixture as the cathode material. The fabricated cell showed an open circuit voltage (OCV) of 0.40V.

Abstrak

PEO telah didopkan dengan sebatian "Organotin" yang terpilih. Pendopan "Organotin" yang digunakan adalah Ph_3SnSCN dan $[\text{Ph}_3\text{SnCl}]^- [\text{Me}_4\text{N}]^+$. Penerapan stannun ke dalam polimer telah sahkan melalui beberapa teknik fizikal. Analisis spektroskopi inframerah bagi filem elektrolit yang didopkan Ph_3SnSCN menunjukkan ikatan pada $2080-2050 \text{ cm}^{-1}$, yang mana ianya juga ditunjukkan oleh kompaun Ph_3SnSCN tulen. Pendopan elektrolit dengan kepekatan organotin yang berlainan disediakan dan kajian kekonduksian ke atasnya dilakukan dengan kaedah impedans spektroskopi. Daripada pengukuran didapati kekonduksian yang terbaik telah dicapai iaitu $7.6 \times 10^{-8} \text{ S/cm}$ dengan hisbah PEO. Garam bresamaan 90:10. Kekonduksian masih dapat ditingkatkan beberapa tertib magnitud dengan penambahan 'plasticizers' seperti etilena karbonat (EC) dan propilena karbonat (PC), dan kekonduksian terbaik yang dicapai ialah 10^{-5}S/cm untuk kompleks polimer-garam-plasticizer. Komponen 'plastisizer' terdiri daripada EC dan PC dalam nisbah 1:1. Analisis pembelauan sinar -X menunjukkan pemusnahan hablur PEO yang berinteraksi dengan pendop tin. Corak keputusan yang sama telah diperolehi dengan tetramethyl ammonium dichlorotriphenylstannate sebagai pendop. Walaubagaimanapun, nilai kekonduksian hanya 10^{-8}Scm^{-1} dan ianya tidak sebaik yang diperolehi dengan sebatian Ph_3SnSCN . Sampel pengkonduksi yang baik dari tripheytin thiocyannate -polimer telah digunakan dalam pempfabrikatan sel pertama dengan logam Sn sebagai anod dan karbon-iodin sebagai katod. Sel ini telah memberikan nilai voltan litar terbuka (OCV) sebanyak 0.40 V.

CONTENTS**Contents**

Acknowledgements

Abstract

Contents

Chapter 1 Introduction

1.1	Background	1
1.2	Polymer	2
1.3	Polymerization	4
1.3.1	Condensation Polymerization	5
1.3.2	Addition Polymerization	5
1.4	Conducting Polymers	7
1.4.1	Electron Conducting Polymers	7
1.4.2	Ion Conducting Polymers	9
1.5	Solvating Polymers	10
1.6	Poly(ethylene Oxide) PEO	12
1.7	PEO Content, Electrical Conductivity and Glass Transition Temperature (T_g)	15
1.8	How Is PEO produced?	16
1.8.1	Low molecular weight Polymer Synthesis	17
1.8.2	High molecular weight Polymer Synthesis	18
1.9	PEO- Salt Complexes	18
1.10	Preparation Techniques of PEO-Salt Complexes	20
1.10.1	Solution Casting method	20
1.10.2	Melt Method	20
1.11	Characteristics of PEO-Salt Complexes	20

1.11.1	Multiphase Behaviour	21
1.11.2	Description of Polymer Structure and Mobility	23
1.11.3	Morphology	23
1.11.4	Ionic Transport Mechanism	24
1.11.4.1	Some Empirical Relationships	24
1.11.4.2	Free Volume Theory And Configurational Entropy Models	26
1.11.4.3	Dynamic Bond Percolation Model: A Microscopic Theory	28
1.12	Phase changes	29
1.13	Mass Transport in Elastomer Phase	29
1.14	Factors which determine the ionic Conductivity	29
1.14.1	Tortuosity Factor	30
1.14.2	Effective Mobile Ion Concentration	30
1.15	Applications of PEO – salt complexes	32
1.15.1	Electrochemical sensors	32
1.15.2	Electrochromic Devices	33
1.15.3	Solid State Batteries	34
1.16	Objectives of the Present Work	36
Chapter 2: Experimental Methods		
2.1	Materials and Methods	38
2.1.1	Starting Materials	38
2.1.2	Synthesis of Triphenyltin Complexes	
2.1.3	Preparation of Polymer Electrolyte Films	39
2.2	Characterization Techniques	40
2.2.1	X-ray Diffraction	41

2.2.2	Infrared Spectroscopy	41
2.2.3	Impedance Spectroscopy	43
2.3	Ionic Transference Number Measurement	46
2.4	Cell characterization and discharge characteristics	47
Chapter 3: Characteristics Of PEO – Ph₃SnSCN complexes		
3.1	Introduction	49
3.2	XRD analysis	49
3.3	IR spectral analysis	54
3.4	Impedance spectroscopy analysis	59
3.4.1	Room temperature dependence of electrical conductivity	59
3.4.2	Complex Permittivity	66
3.4.3	Electrical modulus	69
3.4.4	Temperature Dependence of Electrical conductivity	72
3.5	Possible conduction mechanism	74
3.6	Ionic Transference number measurements	75
3.7	Solid state electrochemical cell fabrication	76
Chapter 4 Characteristics of PEO- [Ph₃SnCl₂]⁻ [Me₄N]⁺ Complexes		
4.1	Introduction	78
4.2	XRD analysis	78
4.3	IR spectral analysis	82
4.4	Impedance spectroscopy	85
4.4.1	Room temperature dependence of electrical Conductivity	85
4.4.2	Temperature dependence of electrical conductivity	91
4.4.3	Complex Permittivity	93
4.4.4	Electrical Modulus	94

4.5 Transference number measurements.	97
Chapter 5	
Summary and conclusion	99
References	102-111