

ABSTRACT

In recent years, the demand for reduced weight and high performance materials for automotive applications such as brake disc have increased. The newly developed, aluminium metal matrix composite (Al-MMC) reinforced with silicon carbide (SiC) particulate seem suitable to be an alternative material for this application. In this experimental study, Al-Cu-SiC_p MMC was developed through stir casting method with sand mould. A constant 4.5% of weight percentage of 5 µm pure copper powder was added to the mixtures to enhance the properties of Al-MMC. The effects of particle sizes of SiC as well as the weight percentage of SiC, pouring temperature and stirring time on the hardness, wear, compressive properties, flexure behavior and density of Al-Cu-SiC_p MMC were investigated. Taguchi's Robust Parametric Design was used with inner array L₉ 3⁴ and outer array with 2 replications to plan the experimental runs. A statistical Pareto Analysis of Variance (Pareto ANOVA) was employed to determine the significant factors of these properties and optimum combinations of process variables for targeted functions. From the analysis, it was found that particle sizes of SiC is the most significant factor for density characteristic and compressive properties while weight percentage of SiC is the most significant factor for hardness and wear resistance characteristics. Optimum combinations were determined and conformity test were conducted to verify the optimum properties of newly developed material, Al-Cu-SiC_p MMC. Optimum combination of hardness was A₁B₂C₀D₀ (59 µm particle size of SiC, 15% of weight percentage of SiC, 675 °C pouring temperature and 5 minutes stirring time) with 82.5 HV; wear rate A₂B₂C₂D₀ (106 µm particle size of SiC, 15% of weight percentage of SiC, 725 °C pouring temperature and 5 minutes stirring time) with 1.585 x 10⁻⁵ g/sec; compressive strength A₁B₂C₂D₁ (59 µm particle size of SiC, 15% of weight percentage of SiC, 725 °C pouring temperature and 10 minutes stirring time) with 9410.06 MPa and density A₀B₁C₁D₁ (40 µm particle size of SiC, 10% of weight percentage of SiC, 700 °C pouring temperature and 10 minutes stirring time) with 2.6592 g/cm³.