



**ELECTRICAL PROPERTIES OF IMPURITY DOPED  
POLY VINYL CHLORIDE**

BY

**REKHA LAKSHMAN RAO**

Dissertation submitted to the University of Malaya in fulfillment for the  
Degree of Masters in Philosophy

*Institute for Post Graduate Studies and Research*

*University of Malaya*

1998

Perpustakaan Universiti Malaya



A505616248

## **Declaration**

I hereby declare that the work reported in this thesis is my own unless specified and duly acknowledged by quotation.

26<sup>th</sup> of May 1998

REKHA LAKSHMAN RAO

PERPUSTAKAAN INSTITUT PENGAJIAN  
SISWAZAH DAN PENYELIDIKAN  
UNIVERSITI MALAYA

## **Acknowledgement**

I wish to express my profound gratitude to Professor S.Radhakrishna, Institute for Postgraduate Research Center and Advanced Studies, University Malaya for his invaluable support, encouragement and guidance, without which this work would not have conceived.

I would also like to thank Associate Professor Abdul Kariem Arof of Center for Foundation Studies in Science, University Malaya for his constant support and guidance.

I would also like to express my real appreciation and thanks to my labmates namely Srinivas, Anandan, Jacob, Sundar and Norhaizan for helping me with laboratory work and technical problems.

Finally, I would like to thank my husband, Anand Shankar for his invaluable support, patience and encouragement throughout this work.

## Abstract

*Poly(vinyl chloride) is a polymer, with very negligible electrical conductivity of the order of  $10^{-8}$  S/cm. In this investigation, PVC has been tried as a host matrix for solvating  $\text{Li}^+$  salts. By dissolving PVC with  $\text{LiClO}_4$ ,  $\text{LiBF}_4$  and  $\text{LiCF}_3\text{SO}_3$  in tetrahydrofuran and casting it into thin films, electrical conductivity can be increased by an order of magnitude. Better conducting films can be obtained by increasing the concentration of the lithium salts in the matrix. The film comprising of 70 wt% PVC and 30 wt% salt exhibits the highest room temperature conductivity of  $1.63 \times 10^{-7}$  S/cm. A plot of electrical conductivity versus salt concentration shows an increase in conductivity upto a certain salt concentration after which conductivity starts to decrease with salt content. This phenomenon can be attributed to the weak electrolyte theory. Amongst all the salts that were added to PVC, the conductivity was better with  $\text{LiClO}_4$  because of its good dissociation capability. Further plasticizers such as ethylene carbonate (EC), propylene carbonate (PC) and a combination of both were added to improve the existing value of the conductivity. A value of  $3.34 \times 10^{-4}$  was obtained with a concentration of 11.7 wt% PVC, 5 wt% of  $\text{LiClO}_4$ , 13.3 wt% of EC and 70 wt% of PC. Thus the plasticizers provide a pathway for the ions to move in the PVC-salt matrix. A solid state battery was fabricated from the polymer electrolyte film with plasticizers and its characteristics were presented and discussed.*

## CONTENTS

<b>1.0</b>	<b>CHAPTER 1 – INTRODUCTION</b>	<b>1</b>
1.1	Polymer	1
1.2	Polymerisation	3
1.2.1	Condensation (Step Reaction) Polymerisation	3
1.2.2	Addition (Chain Reaction) Polymerisation	4
1.3	Conducting Polymers	5
1.4	Electron Conducting Polymers	6
1.5	Ion Conducting Polymers	7
1.6	Polymer Electrolytes	8
1.7	Polyelectrolytes	9
1.8	Gel Electrolytes	10
1.9	Poly (Vinyl Chloride)	10
1.10	Low molecular weight organic solvents	11
1.11	Polymers behave like solids and also like liquids	12
1.12	Description of polymer structure and mobility	14
1.13	Mass transport in elastomer phase	15
1.14	Factors which determine the conductivity	16
1.15	The mechanism of ionic conductivity	19
1.16	Free volume theory and configurational entropy models	22
1.17	Dynamic bond percolation model : A microscopic theory	23

1.18	Methods of introducing ions	24
1.19	Results from earlier work on polymer electrolytes	25
1.20	Aim of present work	31
<b>2.0</b>	<b>CHAPTER 2 – EXPERIMENTAL METHODS</b>	<b>33</b>
2.1	Preparation of polymer electrolyte	33
2.2	Sample characterization	33
2.3	X-Ray Diffraction (XRD)	33
2.4	Scanning Electron Microscope (SEM)	36
2.5	Energy Dispersive Analysis of X-Rays (EDAX)	40
2.6	Impedance Spectroscopy	44
<b>3.0</b>	<b>RESULTS &amp; DISCUSSION – PVC DOPED WITH Li<sup>+</sup> SALTS</b>	<b>51</b>
3.1	AC Conductivity Analysis	51
3.2	XRD Analysis	60
3.3	SEM Analysis	64
3.4	EDAX Analysis	66
<b>4.0</b>	<b>RESULTS &amp; DISCUSSION – PVC DOPED WITH Li<sup>+</sup> SALTS AND PLASTICIZERS</b>	<b>67</b>
4.1	AC Conductivity Analysis	67
4.2	XRD Analysis	82

4.3	SEM Analysis	84
4.4	EDAX Analysis	86
4.5	Electrochemical Cell Fabrication	88
4.6	Electrochemical Cell Characterization	88
5.0	<b>CONCLUSIONS AND SUGGESTIONS FOR FURTHER WORK</b>	89
5.1	Conclusions	89
5.2	Suggestions	89
	<b>REFERENCES</b>	<b>91</b>