

CHAPTER 6
CONCLUSION

CHAPTER 6 CONCLUSIONS

Within the limitations of the study, the conclusions are-

- Filtek Z350 exhibited significantly higher VHN compared to other composites tested.
- VHN of all composites was significantly higher before immersion in mouthrinses except Ceram•X Duo.
- The decrease in VHN was material dependent.
- Plant extract in experimental mouthrinses seem to have an effect on surface microhardness of Ceram•X Mono, however it was not statistically significant.